



Ambi-ance™

Ambidextrous Nitrile Gloves Powder-Free

Maximum comfort and performance with improved dexterity and tactile sensitivity

- Soft stretch Nitrile for a comfortable custom fit.
- Puncture and tear resistant barrier.
- Beaded cuff for extra protection.
- Textured fingertips for exceptional tactile sensitivity and enhanced grip.



Ordering Information

Blue Non-Sterile, 3.5 Gram Weight Available in 5 Convenient Sizes:

Description	Quantity	Ref. #
Extra Small	200/box	19010
Small	200/box	19011
Medium	200/box	19012
Large	200/box	19013
Extra Large	200/box	19014

Meets ASTM D6319 Standards.



CLEARED FOR USE WITH CHEMOTHERAPY DRUGS.

TEST CHEMOTHERAPY DRUG AND CONCENTRATION

- Carboplatin, 10 mg/ml (10,000ppm)
- Carmustine (BCNU), 3.3 mg/ml (3,300 ppm)
- Cisplatin, 1.0 mg/ml (1,000 ppm)
- Cyclophosphamide (Cytoxan), 20.0 mg/ml (20,000 ppm)
- Dacarbazine (DTIC), 10.0 mg/ml (10,000 ppm)
- Doxorubicin Hydrochloride, 2.0 mg/ml (2,000 ppm)
- Etoposide (Toposar) 20.0 mg/ml (20,000 ppm)
- Fluorouracil 50.0 mg/ml (50,000 ppm)
- Ifosfamide, 50.0 mg/ml (50,000 ppm)
- Methotrexate, 25 mg/ml (25,000 ppm)
- Mitomycin C, 0.5 mg/ml (500 ppm)
- Mitoxantrone, 2 mg/ml (2,000 ppm)
- Paclitaxel (Taxol), 6.0 mg/ml (6,000 ppm)
- Thiotepa, 10.0 mg/ml (10,000 ppm)
- Vincristine Sulfate, 1.0 mg/ml (1,000 ppm)

MINIMUM BREAKTHROUGH DETECTION TIME (Specimen 1/2/3) (Minutes)

- No breakthrough up to 240 min.
- 1.82 (3.96, 1.82, 5.98)
- No breakthrough up to 240 min.
- No breakthrough up to 240 min.
- No breakthrough up to 240 min.
- No breakthrough up to 240 min.
- No breakthrough up to 240 min.
- No breakthrough up to 240 min.
- No breakthrough up to 240 min.
- No breakthrough up to 240 min.
- No breakthrough up to 240 min.
- No breakthrough up to 240 min.
- 0.93 (3.09, 5.38, 0.93)
- No breakthrough up to 240 min.

Ambi-ance™ Ambi-dextrous Nitrile Gloves were tested with the above chemotherapy drug concentrations in accordance with ASTM D 6978-05, Standard practice assessment of Resistance of Medical Gloves to Permeation by Chemotherapy drugs. Note: Testing conditions used were intended to approximate the worse case conditions for clinical use. It is the user's responsibility to determine the applicability of these gloves for the intended use with chemotherapy drugs.

